

**RLT-7730**  
**Die Casting Release Agent for**  
**Aluminium, Magnesium and Zinc Die Casting**

**DESCRIPTION:**

RLT-7710/7730/7750 is a stable, water based emulsion, which is ideally suited for the conventional and slightly reduced spray application and even for low-volume spraying (micro-spraying). The reason is the careful selection of certain raw material combinations, ensuring not only the high quality of produced castings but also the problem-free handling of the castings in downstream processes.

Castings are clean, bright and are readily painted or coated and are also suitable for welding or gluing.

The good release effect is guaranteed by the spontaneously forming of a water-repellent film on the die surface. The film adheres well, wherever it is applied and will not be washed off by during application nor blown into outlying parts of the die. Therefore gas entrapment and streaks due to release agent accumulations can be mostly prevented.

Even after many weeks in use, no sticky residue will form on die and frame, pipes of spray systems and nozzles will never block. Core slides and vents will stay clean, allowing air and gas to escape unhindered thus improving the quality of castings (reduced porosity).

## Application

Suitable for a wide spectrum of castings, also for large structural and heavy parts.  
Die temperatures: from about 150 to 380 °C.

The ultimate or ideal dilution ratio for a particular casting is determined by: duration of spray, spray velocity, geometry and complexity of casting as well as the temperature of the tooling. On-site tests should therefore be carried out to establish the correct ratio for each particular application.

RLT-7710/7730/7750 is available in several concentrations, each of them will dissolve in water instantly. Prior to use, RLT-7710/7730/7750 must be diluted with water. Thereafter the diluted product should not be

stirred in order to prevent foaming. Do not use air agitation. Immediately after use, the containers with the release agent concentrate must be closed tightly.

Recommended dilution ratios with tap water:

<b>Product</b>	<b>Aluminium and Magnesium</b>
7710:	1 : 100-120
7730:	1 : 250-300
7750:	1 : 400-500

## Properties and Advantages

- castings are well suitable for joining processes like welding and glueing
- excellent paintability and powder coating ability of castings
- tried and tested on conventional, reduced, as well as micro-spraying
- good die release and good lubrication of ejector pins
- effective reduction of "metallization" (metal-on-metal welding)
- excellent and shiny surfaces of castings
- high process reliability (stable emulsion, no separation, no stirring required)
- clean die frame and environment; no clogging of pipes and spray nozzles

## Chemical and Physical Data

Appearance:	white emulsion
Odour:	characteristic
Density at 20 °C:	0.96 – 0.98
PH-value at 20 °C:	7 - 9
Shelf life:	One year if stored correctly (for further details see Safety Data Sheet)

## Safety

Reference is made to the **Safety Data Sheet** for information on protective measures, current safety, first aid instructions and label warnings when handling this product.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not resolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter specification within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing which we have no control of, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, resolve the matter.